

BIOTECHNOLOGICAL COMPANY

IN ZULAWKA

11 Bukowa Street, 83-010 Rotmanka

Poland

Tel. (48 58) 692 11 87, 692 11 89

LIST OF PHYSICAL AND CHEMICAL DETERMINATIONS OF THE COLLAGEN GEL
FROM SILVER CARP MANUFACTURED ON 23rd FEBRUARY 2004

The analysis was done on the samples No. 4, 5, 6 / 02 / 04 after 90-days storage in the temperatures of 4.3 and 23.7 centigrades.

Hydrocypoline [$\mu\text{g}/\text{cm}^3$]	–	1864 \pm 41
Temperature of denaturization	–	above 23.8 centigrades
pH	–	3.7
Specific gravity [g/cm^3]	–	1.015 \pm 0.007
Dry mass remains	–	2.86 \pm 0.1
Physical and chemical stability:	from 4.3 centigrades	– complete
	to 23.7 centigrades	– complete

WYKONAWCZY ZAKŁAD
INŻYNIERIA
DOKTOR Anna Abikamnet
biotechnologia

.....
Person responsible
for control programme